

TechNiGlove

INTERNATIONAL

PHYSICAL PROPERTIES

Style:	Nonsterile –	Ambidextrous
Length:		12" (300mm)
Thickness:		5 mil (.005")
Grip Surface:		Microtexture Fingertips
Cuff:		Beaded
Color:		White, Green, Blue
Tensile Strength:		12.9 MPa minimum
Elongation:		
	Before Aging	550% minimum
	After Aging	400% minimum

TECHNICAL PROPERTIES

Particle Levels:	<400 total particles/cm ²
(Class M2.5 (10))	IES RP-CC-005.2 Method
ESD Volume Resistance:	5 x 10 ¹⁰ per ESD-511.12-1996
Decay Time:	<0.5 sec. per RETS-5-003 REV A

Extractables

TNVR:	<1.00 µg/cm ²	Silicone:	None
Chloride:	<0.1 µg/cm ²	Amide:	None
Sulfate:	<0.02 µg/cm ²	Phthalates:	None
Nitrate:	<0.1 µg/cm ²	Fluoride:	<0.005 µg/cm ²
Phosphate:	<0.005 µg/cm ²		
Nitrite:	<0.005 µg/cm ²		
Bromide:	<0.02 µg/cm ²		

ORDERING INFORMATION

12" Class 10 Nitrile Gloves

WHITE

		Case Wt.
TNI200W	X-SMALL	17
TNI201W	SMALL	18
TNI202W	MEDIUM	19
TNI203W	LARGE	20
TNI204W	X-LARGE	22
TNI205W	XX-LARGE	23

100 Poly Bag, 10 Bags/Case = 1,000 Gloves/Case, Case Size 13"x12"x13"

BLUE


		Case Wt.
TNI200B	X-SMALL	17
TNI201B	SMALL	18
TNI202B	MEDIUM	19
TNI203B	LARGE	20
TNI204B	X-LARGE	22
TNI205B	XX-LARGE	23

100 Poly Bag, 10 Bags/Case = 1,000 Gloves/Case, Case Size 13"x12"x13"

GREEN

		Case Wt.
TNI200G	X-SMALL	17
TNI201G	SMALL	18
TNI202G	MEDIUM	19
TNI203G	LARGE	20
TNI204G	X-LARGE	22
TNI205G	XX-LARGE	23

100 Poly Bag, 10 Bags/Case = 1,000 Gloves/Case, Case Size 13"x12"x13"



Three Colors for Critical Environment Color Coding

CHEMICAL RESISTANCE GUIDE

Acetic Acid	G	Isobutyl Alcohol	G
Acetone	F	Isooctane	E
Acetonitrile Allyl Alcohol	G	Isopropyl Alcohol	G
Allyl Alcohol	G	Lactic Acid (85%)	E
Amyl Acetate	F	Maleic Acid	E
Amyl Alcohol	E	Methyl Alcohol	P
Butyl Alcohol	E	Methyl Amine	G
Butyl Cellosolve	E	Methyl T-Butyl Ether	P
Carbon Tetrachloride	F	Mineral Spirits	G
Citric Acid (10%)	E	Monoethanolamine	E
Diacetone Alcohol	P	Naptha	F
Dibutyl Phthalate	E	Octanol	E
Dimethyl Sulfoxide	G	Oleic Acid	E
Ethyl Acetate	P	Oxalic Acid	E
Ethyl Alcohol	G	Pentachlorophenol	E
Ethyl Ether	F	Pentane	P
Ethyl Glycol Ether	G	Perchloroethylene	F
Ethylene Glycol	E	Potassium Hydroxide	E
Formaldehyde	F	Propyl Alcohol	G
Gasoline	F	Sodium Hydroxide	E
Hexane	E	Stoddard Solvent	E
Hydrazene (65%)	E	Sulfuric Acid	E
Hydrochloric Acid (10%)	E	Toluene	F
Hydrogen Peroxide	E	Turpentine	G
Hydroquinone	E	Xylene	F

E = Excellent G = Good F = Fair P = Poor

NOTE: The recommendations above are meant as a general guide when selecting gloves for any chemical contact use. TechNiTrile nitrile gloves are dipped thin for dexterity and comfort. The trade-off in emphasizing these qualities is the fact that the gloves provide only a limited degree of chemical "splash" protection. They do not provide the high degree of chemical protection found in heavier weight gloves designed specifically for chemical use.

TechNiGlove

INTERNATIONAL

3750 Pierce Street • Riverside, CA 92503 • USA

Toll Free: 1-877-648-7453

Phone: 951-582-0890

Fax: 951-582-0990

Visit us on the web at www.Techniglove.com