

TechNiGlove

INTERNATIONAL

PHYSICAL PROPERTIES

Style: Non-Sterile	Ambidextrous
Length: TN1000	12" (300mm)
TN300	9.5" (240mm)
Thickness:	5 mil (.005")
Grip Surface:	Microtextured Fingertips
Cuff:	Beaded
Color: TN1000	White, Blue or White <u>Tacky</u>
TN300	White or Blue
Tensile Strength:	12.9 MPa minimum

TECHNICAL PROPERTIES

Particle Levels: TN1000	<2500 total particles/cm ² >0.5µm
TN300	<2500 total particles/cm ² >0.5µm
Electrical Properties Resistivity:	At 12.5% R. Humidity 1x10 ⁸ ohm/square per ESD-S11.12
Static Decay:	At 12.5% R. Humidity <3 seconds per RETS-5-003
Total Non Volatile Residue:	4.0 µg/cm ²

Extractables

Silicone:	None	Sulfate (SO ₄ ²⁻):	<0.05 µg/cm ²
Amide:	None	Lithium (Li ⁺):	<0.005 µg/cm ²
Phthalates:	None	Sodium (Na ⁺):	<0.05 µg/cm ²
Fluoride (F ⁻):	<0.05 µg/cm ²	Ammonium (NH ₄ ⁺):	<0.05 µg/cm ²
Chloride (Cl ⁻):	<0.400 µg/cm ²	Potassium (K ⁺):	<0.05 µg/cm ²
Bromide (Br ⁻):	<0.05 µg/cm ²	Magnesium (Mg ²⁺):	<0.05 µg/cm ²
Nitrate (NO ₃ ⁻):	<2.00 µg/cm ²	Calcium (Ca ²⁺):	<0.05 µg/cm ²
Phosphate (PO ₄ ³⁻):	<0.05 µg/cm ²		

ORDERING INFORMATION

12" Class 100 White or Blue, Nitrile Gloves

		Case Wt.
TN1000 (W)(B)	X-SMALL	15 lbs.
TN1001 (W)(B)	SMALL	18 lbs.
TN1002 (W)(B)	MEDIUM	19 lbs.
TN1003 (W)(B)	LARGE	19 lbs.
TN1004 (W)(B)	X-LARGE	22 lbs.
TN1005 (W)(B)	XX-LARGE	23 lbs.

100 Poly Bag, 10 Bags/Case = 1,000 Gloves/Case - Case size 13"x12"x13"

12" Class 100 White Tacky Nitrile Gloves For Enhanced Grip

		Case Wt.
TN1000WT	X-SMALL	15 lbs.
TN1001WT	SMALL	18 lbs.
TN1002WT	MEDIUM	19 lbs.
TN1003WT	LARGE	19 lbs.
TN1004WT	X-LARGE	22 lbs.
TN1005WT	XX-LARGE	23 lbs.

100 Poly Bag, 10 Bags/Case = 1,000 Gloves/Case - Case size 13"x12"x13"

9.5" Class 100 White or Blue, Nitrile Gloves

		Case Wt.
TN300 (W)(B)	X-SMALL	13 lbs.
TN301 (W)(B)	SMALL	14 lbs.
TN302 (W)(B)	MEDIUM	15 lbs.
TN303 (W)(B)	LARGE	16 lbs.
TN304 (W)(B)	X-LARGE	18 lbs.

100 Poly Bag, 10 Bags/Case = 1,000 Gloves/Case - Case size 11"x13"x11"



CHEMICAL RESISTANCE GUIDE

Acetic Acid	G	Isobutyl Alcohol	G
Acetone	F	Isooctane	E
Acetonitrile	F	Isopropyl Alcohol	G
Allyl Alcohol	G	Lactic Acid (85%)	E
Amyl Acetate	F	Maleic Acid	E
Amyl Alcohol	E	Methyl Alcohol	P
Butyl Alcohol	E	Methyl Amine	G
Butyl Cellosolve	E	Methyl T-Butyl Ether	P
Carbon Tetrachloride	F	Mineral Spirits	G
Citric Acid (10%)	E	Monoethanoline	E
Diacetone Alcohol	P	Naphtha	F
Dibutyl Phthalate	E	Octanol	E
Dimethyl Sulfoxide	G	Oleic Acid	E
Ethyl Acetate	P	Oxalic Acid	E
Ethyl Alcohol	G	Pentachlorophenol	E
Ethyl Ether	F	Pentane	P
Ethyl Glycol Ether	G	Perchloroethylene	F
Ethylene Glycol	E	Potassium Hydroxide	E
Formaldehyde	F	Propyl Alcohol	G
Gasoline	F	Sodium Hydroxide	E
Hexane	E	Stoddard Solvent	E
Hydrazene (65%)	E	Sulfuric Acid	E
Hydrochloric Acid (10%)	E	Toluene	F
Hydrogen Peroxide (30%)	E	Turpentine	G
Hydroquinone	E	Xylene	F

E = Excellent G = Good F = Fair P = Poor

NOTE: The recommendations above are meant as a general guide when selecting gloves for any chemical contact use. TechNiTrile nitrile gloves are dipped thin for dexterity and comfort. The trade-off in emphasizing these qualities is the fact that the gloves provide only a limited degree of chemical "splash" protection. They do not provide the high degree of chemical protection found in heavier weight gloves designed specifically for chemical use.

TechNiGlove

INTERNATIONAL

3750 Pierce St. • Riverside, CA 92503 • USA

Toll Free: 1-877-648-745

Phone: 951-582-0890

Fax: 951-582-0990

Visit us on the web at www.Techniglove.com